

Description	Unit	Minimum	Maximum	Note
I-Materials composition 1 SiO _x PET//NYL//CPP 2 AlO _x PET//NYL//CPP	Micron "	12//15//50 12//15//50	12//25//100 12//25//100	EASY PEEL SEALANT IS AVAILABLE.
II-Printing Characteristics Printing type Colour printed	Reverse –	0	8	ROTOGRAVURE PRINTED.
III-Product's Dimension Reel Width Length Paper Core Weight/Roll	mm. mtr. mm. kgs.	140 500 3 –	320 1,000 6 80	
IV-Bond Strength PET//NYL+CPP PET+NYL//CPP	kgf/15mm "	0.50 0.70	– –	
V-Seal Strength ≥50 Micron CPP ≥80 Micron CPP ≥100 Micron CPP	kgf/15mm " "	5.00 5.50 6.00	– – –	
VI-O₂TR (Oxygen transmission rate)	cc/m ² /24	–	0.003	
VII-WVTR (Water vapour transmission rate)	gm/m ² /24	–	0.005	
VIII-Retort Conditions Temperature Time Pressure	°C Minute Bar	– – –	123 30 5	
IX-Product Shelf life	Months	–	18	
X-Packing	pcs/pack	1	–	EACH ROLL PACK.
XI-Minimum order quantity (MOQ)	Pcs	50	–	DEPEND ON SIZE.
XII-Lead time	Day	30	60	

XIII-Important Notice;

All above data is a range of standard was measured, product characteristics can be change by thickness or materials compositions. Please request on your needs.