

Description	Unit	Minimum	Maximum	Note
I-Materials composition				
1 PET//ALU//NYL//CPP	Micron	12//7//15//50	12//9//25//100	EASY PEEL SEALENT IS AVAILABLE.
2 PET//NYL//ALU//CPP	Micron	12//15//7//50	12//25//9//100	
II-Printing Characteristics				
Printing type	Reverse			ROTOGRAVURE PRINTED.
Colour printed	–	0	8	
III-Product's Dimension				
Reel Width	mm.	140	320	
Length	mtr.	500	1,000	
Paper Core	mm.	3	6	
Weight/Roll	kgs.	–	80	
IV-Bond Strength				
PET//NYL+ALU+CPP	kgf/15mm	0.50	–	UNABLE TO PEEL.
PET+NYL//ALU+CPP	"	–	–	
PET+NYL+ALU//CPP	"	0.60	–	
V-Seal Strength				
≥50 Micron CPP	kgf/15mm	5.00	–	
≥80 Micron CPP	"	5.50	–	
≥100 Micron CPP	"	6.00	–	
VI-O₂TR (Oxygen transmission rate)	cc/m ² /24	–	0.001	
VII-WVTR (Water vapour transmission rate)	gm/m ² /24	–	0.001	
VIII-Retort Conditions				
Temperature	°C	–	125	
Time	Minute	–	45	
Pressure	Bar	–	5	
IX-Product Shelf life	Months	–	24	
X-Packing	pcs/pack			EACH ROLL PACK.
XI-Minimum order quantity (MOQ)	Pcs	50	–	DEPEND ON SIZE.
XII-Lead time	Day	30	60	

XIII-Important Notice;

All above data is a range of standard was measured, product characteristics can be change by thickness or materials compositions. Please request on your needs.